

Pavia University



The Guided-Mode Expansion Method for Photonic Crystal Slabs

Lucio Claudio Andreani

Dipartimento di Fisica "Alessandro Volta," Università degli Studi di Pavia, via Bassi 6, 27100 Pavia, Italy

andreani@fisicavolta.unipv.it http://fisicavolta.unipv.it/dipartimento/ricerca/fotonici/

COST P11 Training School, Univ. of Nottingham, June 19-22, 2006

Acknowledgements

Collaboration:

Mario Agio (now at Physical Chemistry Laboratory, ETH-Zurich)Dario Gerace (now at Institute of Quantum Electronics, ETH Zurich)

Support:

MIUR (Italian Ministry for Education, University and Research) under Cofin program "Silicon-based photonic crystals" and FIRB project "Miniaturized electronic and photonic systems"

INFM (National Institute for the Physics of Matter) under PRA (Advanced Research Project) "PHOTONIC"



Ministero dell'Istruzione dell'Università e Ricerca



Fisica della Materia

Outline

1. Required notions

- ·Basic properties of photonic band structure
- •Plane-wave expansion
- •Dielectric slab waveguide
- •Waveguide-embedded photonic crystals

2. Guided-mode expansion method

- Photonic mode dispersion
- Intrinsic diffraction losses
- •Convergence tests, comparison with other methods
- •Examples of applications

Photonic crystals are materials in which the dielectric constant is periodic in 1D, 2D or 3D...



Figure 1 Simple examples of one-, two-, and three-dimensional photonic crystals. The different colors represent materials with different dielectric constants. The defining feature of a photonic crystal is the periodicity of dielectric material along one or more axes.

... leading to the formation of photonic bands and gaps.



Figure 2 The photonic band structures for on-axis propagation, shown for three different multilayer films, all of which have layers of width 0.5*a*. Left: each layer has the same dielectric constant $\varepsilon = 13$. Center: layers alternate between $\varepsilon = 13$ and $\varepsilon = 12$. Right: layers alternate between $\varepsilon = 13$ and $\varepsilon = 1$.

- A full photonic band gap in 3D may allow to achieve • suppression of spontaneous emission (*E. Yablonovitch, 1987*)
- localization of light by disorder (*S. John, 1987*)

Books:

Joannopoulos JD, Meade RD and Winn JN, *Photonic Crystals – Molding the Flow of Light* (Princeton University Press, Princeton, 1995).

Johnson SG and Joannopoulos JD, *Photonic Crystals: the Road from Theory to Practice* (Kluwer Academic Publishers, Boston, 2001).

Sakoda K: *Optical Properties of Photonic Crystals,* Springer Series in Optical Sciences, Vol. **80**. (Springer, Berlin, 2001).

Busch K, Lölkes S, Wehrspohn RB, Föll H: *Photonic Crystals – Advances in Design, Fabrication and Characterization* (Wiley-VCH, Weinheim, 2004).

Lourtioz JM, Benisty H, Berger V, Gérard JM, Maystre D, Tchelnokov A: *Photonic Crystals: Towards Nanoscale Photonic Devices* (Springer, Berlin, 2005).

Maxwell equations in matter

no sources, unit magnetic permebility

First-order, time-dependent:

$$\nabla \times \mathbf{E} = -\frac{1}{c} \frac{\partial \mathbf{B}}{\partial t}$$
$$\nabla \times \mathbf{H} = \frac{1}{c} \frac{\partial \mathbf{D}}{\partial t}$$
$$\nabla \cdot \mathbf{D} = 0$$
$$\nabla \cdot \mathbf{B} = 0$$
$$\mathbf{D}(\mathbf{r}) = \varepsilon(\mathbf{r})\mathbf{E}(\mathbf{r})$$
$$\mathbf{H}(\mathbf{r}) = \mathbf{B}(\mathbf{r})$$

Second-order, harmonic time dependence $\psi(t) = \psi e^{-i\omega t}$:

$$\nabla \times \nabla \times \mathbf{E}(\mathbf{r}) = \frac{\omega^2}{c^2} \varepsilon(\mathbf{r}) \mathbf{E}(\mathbf{r})$$
$$\nabla \cdot [\varepsilon(\mathbf{r}) \mathbf{E}(\mathbf{r})] = 0$$
$$\mathbf{H}(\mathbf{r}) = -i\frac{c}{\omega} \nabla \times \mathbf{E}(\mathbf{r})$$
$$\nabla \times \left[\frac{1}{\varepsilon(\mathbf{r})} \nabla \times \mathbf{H}(\mathbf{r})\right] = \frac{\omega^2}{c^2} \mathbf{H}(\mathbf{r})$$
$$\nabla \cdot \mathbf{H}(\mathbf{r}) = 0$$
$$\mathbf{E}(\mathbf{r}) = i\frac{c}{\omega} \frac{1}{\varepsilon(\mathbf{r})} \nabla \times \mathbf{H}(\mathbf{r})$$

Translational invariance

If the photonic lattice is invariant under translations by the vectors ${\bf R}$ of a Bravais lattice,

$$\mathcal{E}(\mathbf{r}+\mathbf{R})=\mathcal{E}(\mathbf{r}),$$

then Bloch-Floquet theorem holds for any component of the fields:

$$\psi_{n\mathbf{k}}(\mathbf{r}) = e^{i\mathbf{k}\cdot\mathbf{r}}u_{n\mathbf{k}}(\mathbf{r}), \quad u_{n\mathbf{k}}(\mathbf{r}+\mathbf{R}) = u_{n\mathbf{k}}(\mathbf{r})$$

The frequencies are grouped into *photonic bands*:

$$\omega = \omega_n(\mathbf{k})$$

N.b. the system is assumed to be *infinitely extended* along the directions of periodicity \rightarrow the Bloch vector **k** is *real*.

It is usually chosen to lie in the first Brillouin zone (band folding).

Eigenvalue problem & scale invariance

$$\nabla \times \left[\frac{1}{\varepsilon(\mathbf{r})} \nabla \times \mathbf{H}(\mathbf{r})\right] = \frac{\omega^2}{c^2} \mathbf{H}(\mathbf{r})$$



Hermitian eigenvalue problem (like for electron states in quantum mechanism)

$$\mathbf{r} \to \mathbf{r}' = s\mathbf{r}, \quad \varepsilon'(\mathbf{r}') = \varepsilon(\mathbf{r})$$

 $\Rightarrow \omega_n'(\mathbf{k}') = \frac{\omega_n(\mathbf{k})}{s}$
 $\varepsilon(\mathbf{r})$
 $\varepsilon(\mathbf{r}')$

Scale invariance: photonic band structure is unique when expressed in dimensionless units $\omega a/(2\pi c)$ versus *ka* (*a*=lattice constant)

1. Required notions

- ·Basic properties of photonic band structure
- Plane-wave expansion
- Dielectric slab waveguide
- Waveguide-embedded photonic crystals

2. Guided-mode expansion method

- Photonic mode dispersion
- Intrinsic diffraction losses
- Convergence tests, comparison with other methods
- Examples of applications

Plane-wave expansion in 3D

Expansion of the magnetic field in plane waves with reciprocal lattice vectors **G**:

$$\mathbf{H}_{n\mathbf{k}}(\mathbf{r}) = \sum_{\mathbf{G},\lambda} c_n(\mathbf{k} + \mathbf{G},\lambda) \widehat{\varepsilon}(\mathbf{k} + \mathbf{G},\lambda) e^{\mathbf{i}(\mathbf{k} + \mathbf{G})\cdot\mathbf{r}}$$

where $\hat{\varepsilon}(\mathbf{k} + \mathbf{G}, \lambda) \equiv \hat{\varepsilon}_{\lambda}, \lambda = 1,2$ are two orthogonal unit vectors perpendicular to $\mathbf{k}+\mathbf{G}$. The second-order equation for **H** becomes:

• /•

 \sim

$$\sum_{\mathbf{G}'\lambda'} H_{\mathbf{k}+\mathbf{G},\lambda;\mathbf{k}'+\mathbf{G}',\lambda'c_n}(\mathbf{k}+\mathbf{G}',\lambda') = \frac{\omega^2}{c^2} c_n(\mathbf{k}+\mathbf{G},\lambda)$$
$$H_{\mathbf{k}+\mathbf{G},\lambda;\mathbf{k}+\mathbf{G}',\lambda'} = |\mathbf{k}+\mathbf{G}| |\mathbf{k}+\mathbf{G}'| \varepsilon^{-1}(\mathbf{G},\mathbf{G}') \begin{bmatrix} \hat{\varepsilon}_2 \cdot \hat{\varepsilon}_2' & -\hat{\varepsilon}_2 \cdot \hat{\varepsilon}_1' \\ -\hat{\varepsilon}_1 \cdot \hat{\varepsilon}_2' & \hat{\varepsilon}_1 \cdot \hat{\varepsilon}_1' \end{bmatrix}$$

with the inverse dielectric matrix being defined as (v=unit cell volume)

$$\varepsilon^{-1}(\mathbf{G},\mathbf{G}') = \frac{1}{v} \int \varepsilon^{-1}(\mathbf{r}) e^{i(\mathbf{G}'-\mathbf{G})\cdot\mathbf{r}} d\mathbf{r},$$

Choice of plane waves

The infinite sum over G is truncated to a finite number N of reciprocal lattice vectors, usually chosen by introducing a wavevector cutoff:

$|G| < \Lambda$

The dimension of the linear eigenvalue problem is (2N)x(2N). The matrix *H* is

- * real symmetric if $\varepsilon(\mathbf{r})$ has a center of inversion (taken to be the origin)
- * complex hermitian if $\varepsilon(\mathbf{r})$ has no center of inversion

N.b. The cut-off condition restricts the numbers N to be used: e.g., for the fcc lattice, $N=1,9,15, \ldots$ If other values of N are chosen, unphysical splittings at k=0 may arise

Direct and inverse dielectric matrix

$$\varepsilon(\mathbf{G},\mathbf{G}') = \frac{1}{v} \int \varepsilon(\mathbf{r}) \, \mathrm{e}^{i(\mathbf{G}'-\mathbf{G})\cdot\mathbf{r}} d\mathbf{r} \tag{1}$$

$$\varepsilon^{-1}(\mathbf{G},\mathbf{G}') = \frac{1}{\nu} \int \varepsilon^{-1}(\mathbf{r}) \, \mathrm{e}^{i(\mathbf{G}'-\mathbf{G})\cdot\mathbf{r}} d\mathbf{r}$$
(2)

In the limit $N \rightarrow \infty$, it is equivalent to evaluate $\varepsilon^{-1}(\mathbf{G}, \mathbf{G}')$ from (2) or as a numerical inversion of the direct dieletric matrix (1):

$$\varepsilon^{-1}(\mathbf{G},\mathbf{G}') = [\varepsilon(\mathbf{G},\mathbf{G}')]^{-1}$$

Ho, Chan and Soukoulis, PRL 65, 3152 (1990)

However, the two procedures have different convergence properties for finite *N*.

The procedure by Ho, Chan and Soukoulis generally yields much faster convergence as a function of *N*.

Fourier factorization rules

Consider the Fourier transform *A* of a product of functions *B* and *C*:

$$A_G = \sum_{G'=-\infty}^{+\infty} B_{G-G'} C_{G'}$$

When the sum is truncated to a finite number N of harmonics, the above expression does not converge uniformly if both B and C are discontinuous at the same point while A=BC remains continuous. In this case the inverse rule yields uniform convergence and should be used:

$$A_G = \sum_{G'=-M}^{+M} \left(\frac{1}{B}\right)_{G-G'}^{-1} C_{G'}$$

In the presence of a sharp discontinuity of $\varepsilon(\mathbf{r})$, expressions like $\varepsilon \mathbf{E}$ should be treated according to the direct (inverse) rule when the continuous (discontinuous) component E_{\parallel} (E_{\perp}) of the field is involved.

L.F. Li, JOSA A 13, 1870 (1996); P. Lalanne, PRB 58, 9801 (1998); S.G. Johnson and J.D. Joannopoulos, Opt. Expr. 8, 173 (2001); A. David et al., PRB 73, 075107 (2006)

Complete photonic band gap in 3D: the diamond lattice of dielectric spheres



Figure 3 The photonic band structure for the lowest six bands of a diamond lattice of air spheres in a high dielectric ($\varepsilon =$ 13) material. The wave vector varies across the irreducible Brillouin zone, from Γ to X to W to K, then back to Γ through X, U, and L. See appendix B for a discussion of the Brillouin zone for a face-centered cubic lattice.

K.M. Ho, C.T. Chan and C.M. Soukoulis, Phys. Rev. Lett. 65, 3152 (1990)

2D photonic crystals: parity separation



Plane-wave expansion in 2D

The expansion of the field contains 2D vectors **k** and **G**:

$$\mathbf{H}_{n\mathbf{k}}(\mathbf{r}) = \sum_{\mathbf{G},\lambda} c_n(\mathbf{k} + \mathbf{G},\lambda) \widehat{\varepsilon}(\mathbf{k} + \mathbf{G},\lambda) e^{\mathbf{i}(\mathbf{k} + \mathbf{G}) \cdot \mathbf{I}}$$

The polarization vectors can be chosen as:

 $\hat{\varepsilon}(\mathbf{k} + \mathbf{G}, 1) \equiv \hat{z}, \qquad \hat{\varepsilon}(\mathbf{k} + \mathbf{G}, 2) \equiv \hat{z} \times \hat{k}$

Thus the (2N)x(2N) matrix of the eigenvalue problem decouples as:

$$H_{\mathbf{k}+\mathbf{G},\lambda;\mathbf{k}+\mathbf{G}',\lambda'} = \varepsilon^{-1}(\mathbf{G},\mathbf{G}') \begin{bmatrix} (\mathbf{k}+\mathbf{G})\cdot(\mathbf{k}+\mathbf{G}') & 0\\ 0 & |\mathbf{k}+\mathbf{G}||\mathbf{k}+\mathbf{G}'| \end{bmatrix}$$

where the upper (lower) block corresponds to H (E) modes.

N.b. off-plane propagation, $k_{y} \neq 0$: no parity separation, 3D PWE



Gap for H (TE) modes favoured by connected dielectric lattice (veins) Gap for E (TM) modes favoured by dielectric columns (pillars)

Complete photonic gap in 2D



Gap maps of triangular and graphite lattices



triangular (holes)

Figure 4 Gap map for a triangular lattice of air columns drilled in a dielectric medium, $\varepsilon = 11.4$.

graphite (pillars)



Figure 5 Gap map for a honeycomb lattice of dielectric columns, $\varepsilon = 11.4$.

Gap for H (TE) modes favoured by connected dielectric lattice (holes) Gap for E (TM) modes favoured by dielectric columns

1. Required notions

- Basic properties of photonic band structure
- •Plane-wave expansion
- •Dielectric slab waveguide
- Waveguide-embedded photonic crystals

2. Guided-mode expansion method

- Photonic mode dispersion
- Intrinsic diffraction losses
- •Convergence tests, comparison with other methods
- •Examples of applications

Books

Yariv A., *Quantum Electronics* (Wiley, New York, 1989).

Yariv A. and Yeh P., Optical Waves in Crystals (Wiley, New York, 1984).

Marcuse D., *Light Transmission Optics* (Van Nostrand Reinhold, New York, 1982)

Marcuse D., *Theory of Dielectric Optical Waveguides*, 2nd ed. (Academic Press, New York, 1991)

Dielectric slab waveguide



Leaky vs. guided modes



Dielectric slab waveguide: polarizations

Taking the in-plane wavevector $\mathbf{k} = k_x \hat{x}$, the *xz* plane is a mirror plane and specular reflection $\hat{\sigma}_{xz}$ is a symmetry operation (even if the slab is asymmetric in the vertical direction). Thus all modes (leaky and guided) separate into



TE guided modes

TE modes: E_v, H_x, H_z

(odd under $\hat{\sigma}_{xz}$)

The transverse field component E_{y} , assuming $E_{y}(\mathbf{r},t) = e^{i(k_{x}x - \omega t)}E_{y}(z)$, is found as



$$E_{y}(z) = \begin{cases} A_{3}e^{-\chi_{3}(z-d/2)}, & \chi_{3} = (k_{x}^{2} - \varepsilon_{3}\frac{\omega^{2}}{c^{2}})^{1/2} & z > \frac{d}{2} \\ A_{2}e^{iqz} + B_{2}e^{-iqz}, & q = (\varepsilon_{2}\frac{\omega^{2}}{c^{2}} - k_{x}^{2})^{1/2} & |z| < \frac{d}{2} \\ B_{1}e^{\chi_{1}(z+d/2)}, & \chi_{1} = (k_{x}^{2} - \varepsilon_{1}\frac{\omega^{2}}{c^{2}})^{1/2} & z < -\frac{d}{2} \end{cases}$$

Continuity of E_y , H_x , H_z leads to the implicit equation $q(\chi_1 + \chi_3)\cos(qd) + (\chi_1\chi_3 - q^2)\sin(qd) = 0$ Relation between coefficients: *transfer-matrix method*

TM guided modes

The transverse field component H_{y} , assuming $H_{y}(\mathbf{r},t) = e^{i(k_{x}x - \omega t)}H_{y}(z)$, is found as



$$H_{y}(z) = \begin{cases} C_{3}e^{-\chi_{3}(z-d/2)}, & \chi_{3} = (k_{x}^{2} - \varepsilon_{3}\frac{\omega^{2}}{c^{2}})^{1/2} & z > \frac{d}{2} \\ C_{2}e^{iqz} + D_{2}e^{-iqz}, & q = (\varepsilon_{2}\frac{\omega^{2}}{c^{2}} - k_{x}^{2})^{1/2} & |z| < \frac{d}{2} \\ D_{1}e^{\chi_{1}(z+d/2)}, & \chi_{1} = (k_{x}^{2} - \varepsilon_{1}\frac{\omega^{2}}{c^{2}})^{1/2} & z < -\frac{d}{2} \end{cases}$$

Continuity of H_y , E_x , $D_z = \epsilon E_z$ leads to the implicit equation

$$\frac{q}{\varepsilon_2}\left(\frac{\chi_1}{\varepsilon_1} + \frac{\chi_3}{\varepsilon_3}\right)\cos(qd) + \left(\frac{\chi_1}{\varepsilon_1}\frac{\chi_3}{\varepsilon_3} - \frac{q^2}{\varepsilon_2^2}\right)\sin(qd) = 0$$

Mode dispersion and effective index



General features of waveguide dispersion

•TM modes have higher frequencies than TE modes of the same order

•Symmetric waveguide: no cutoff for lowest-order TE and TM modes (⇒ there is at least one confined photonic state at each frequency and for each polarization)

•Asymmetric waveguide: finite cutoffs even for lowest-order TE and TM modes, all cutoffs are polarization-dependent

•Effective mode index increases smoothly from cladding refractive index (close to cutoff, guided mode extends into claddings) to core refractive index (at large wavevectors, guided mode is well confined)

1. Required notions

- •Basic properties of photonic band structure
- •Plane-wave expansion
- •Dielectric slab waveguide
- Waveguide-embedded photonic crystals

2. Guided-mode expansion method

- •Photonic mode dispersion
- Intrinsic diffraction losses
- ·Convergence tests, comparison with other methods
- •Examples of applications

2D photonic crystals embedded in planar waveguides (photonic crystal slabs)

GaAs membrane (*air bridge*) Chow et al., Nature **407**, 983 (2000) **GaAs/AlGaAs PhC slab with internal source** H. Benisty et al, IEEE J. Lightwave Technol. **17**, 2063 (1999)



Photonic crystal slabs: structures



Photonic crystal slabs: the light-line issue

- Only modes that lie below the light line of the cladding material are guided with no intrinsic losses → truly guided modes.
- Modes that lie *above the light line* have an intrinsic loss mechanism due to out-of-plane diffraction → *quasi-guided modes*.
- The issue of *losses* (intrinsic vs. extrinsic) is a crucial one for prospective applications of PhC slabs to integrated optics.



1. Required notions

- •Basic properties of photonic band structure
- Plane-wave expansion
- Dielectric slab waveguide
- Waveguide-embedded photonic crystals

2. Guided-mode expansion method

- Photonic mode dispersion
- Intrinsic diffraction losses
- •Convergence tests, comparison with other methods
- Examples of applications

Basic idea of guided-mode expansion

Photonic crystal slabs combine the features of



Slab waveguides: control of light propagation in the vertical (z) direction by total internal reflection



 \Rightarrow represent the electromagnetic field as a combination of 2D plane waves in *xy* and guided modes along *z*

General eigenvalue problem

• Equation for the magnetic field:

$$\nabla \times \left(\frac{1}{\varepsilon(\mathbf{r})} \nabla \times \mathbf{H}(\mathbf{r})\right) = \frac{\omega^2}{c^2} \mathbf{H}(\mathbf{r})$$

with the transversality condition $\nabla \cdot \mathbf{H} = 0$.

• Expand magnetic field in a set of basis states as $\mathbf{H}(\mathbf{r}) = \sum_{\mu} c_{\mu} \mathbf{H}_{\mu}(\mathbf{r})$,

orthonormal according to $\int \mathbf{H}_{\mu}^{*}(\mathbf{r}) \cdot \mathbf{H}_{\nu}(\mathbf{r}) d\mathbf{r} = \delta_{\mu\nu}.$

• We obtain a linear eigenvalue problem with a "Hamiltonian" matrix,

$$\sum_{V} H_{\mu V} c_{V} = \frac{\omega^{2}}{c^{2}} c_{\mu}$$
$$H_{\mu V} = \int \varepsilon^{-1}(\mathbf{r}) (\nabla \times \mathbf{H}_{\mu}^{*}(\mathbf{r})) \cdot (\nabla \times \mathbf{H}_{V}(\mathbf{r})) d\mathbf{r}$$

whose eigenvalues and eigenvectors give the photonic band dispersion and magnetic field, respectively.

Electric field and normalization

Once the magnetic field is obtained, the electric field is calculated as

$$\mathbf{E}(\mathbf{r}) = i \frac{c}{\omega} \frac{1}{\varepsilon(\mathbf{r})} \nabla \times \mathbf{H}(\mathbf{r}).$$

The eigenmodes $E_{\rm n}(r), H_{\rm n}(r)$ of the electromagnetic field are orthonormal according to

$$\int \mathbf{H}_{n}^{*}(\mathbf{r}) \cdot \mathbf{H}_{m}(\mathbf{r}) d\mathbf{r} = \delta_{nm},$$

$$\int \mathbf{E}_{n}^{*}(\mathbf{r}) \cdot \mathbf{E}_{m}(\mathbf{r}) \varepsilon(\mathbf{r}) d\mathbf{r} = \delta_{nm}.$$

Physical meaning: the e.m. field energy of an eigenmode is equally shared between the electric and magnetic fields.

The same relations can be used for second quantization of the fields: see C.K. Carniglia and L. Mandel, Phys. Rev. D 3, 280 (1971).

Effective waveguide

We consider a PhC slab with semi-infinite claddings. For the basis states $H_{\mu}(\mathbf{r})$, we choose the guided modes of an effective homogeneous waveguide with an average dielectric constant $\overline{\varepsilon}_{j}$ in each layer j=1,2,3.



We usually take $\overline{\varepsilon}_j$ to be the spatial average of $\varepsilon_j(xy) \equiv \varepsilon_j(\rho)$ in each layer:

$$\overline{\varepsilon}_{j} = \frac{1}{A} \int_{\text{cell}} \varepsilon_{j}(\mathbf{\rho}) d\mathbf{\rho},$$

A=unit cell area

The average dielectric constants must fulfill $\bar{\varepsilon}_2 > \bar{\varepsilon}_1, \bar{\varepsilon}_3$.

Expansion in the basis of guided modes

$$\mathbf{H}_{\mathbf{k}}(\mathbf{r}) = \sum_{\mathbf{G},\alpha} c(\mathbf{k} + \mathbf{G},\alpha) \mathbf{H}_{\mathbf{k}+\mathbf{G},\alpha}^{\text{guided}}(\mathbf{r})$$

k = Bloch vector, chosen to be in the first Brillouin zone

G = reciprocal lattice vectors of the 2D Bravais lattice

 α = index of guided mode

 $H_{k+G,\alpha}^{guided}(\mathbf{r})$ = guided modes of effective waveguide at k+G

Dimension of linear eigenvalue problem is $(N_{PW} N_{\alpha}) \times (N_{PW} N_{\alpha})$.

Since the guided modes are simple trigonometric functions, the matrix elements can be calculated analytically.

Both TE and TM guided modes appear in the expansion of a PhC slab mode. The index α includes mode order and polarization.

Matrix elements: the dielectric tensor

The matrix elements between guided modes depend on the inverse dielectric matrices in the three layers,

$$\eta_j(\mathbf{G},\mathbf{G}') = \frac{1}{A} \int \varepsilon_j^{-1}(\mathbf{\rho}) e^{i(\mathbf{G}'-\mathbf{G})\cdot\mathbf{\rho}} d\mathbf{\rho}$$

Like in 2D plane-wave expansion, they are evaluated from numerical inversion of the direct dielectric matrices:

$$\eta_j(\mathbf{G},\mathbf{G}') = [\varepsilon_j(\mathbf{G},\mathbf{G}')]^{-1}$$

$$\mathcal{E}_{j}(\mathbf{G},\mathbf{G}') = \frac{1}{A} \int \mathcal{E}_{j}(\mathbf{\rho}) e^{i(\mathbf{G}'-\mathbf{G})\cdot\mathbf{\rho}} d\mathbf{\rho}$$

Convergence properties, possible optimization beyond the Ho-Chan-Soukoulis procedure are similar to 2D plane-wave expansion.

The off-diagonal components of $\eta_j(\mathbf{G},\mathbf{G}')$ are responsible for the folding of photonic bands in the first BZ, gap formation, splittings etc.

Discussion of GME method (dispersion)

Main drawback: the basis set of guided modes of the effective waveguide is not complete, since leaky modes are not included

\Rightarrow the GME method is an APPROXIMATE one

Main advantage: folded photonic modes in the first Brillouin zone may fall above the light line \Rightarrow guided and quasi-guided photonic modes are obtained, without the need of introducing any artificial layers (PML...) in the vertical direction.

When a few guided modes are sufficient, as it often happens, the numerical effort is comparable to that of a 2D plane-wave calculation. Very suited for parameter optimization, design...

The dispersion of photonic bands in a PhC slab can be compared with that of the ideal 2D system and with the dispersion of free waveguide modes. Multimode slabs are naturally treated.

Symmetry properties, TE/TM mixing

When the PhC slab is symmetric under reflection in the xy plane: separation of even (σ_{xv} =+1) and odd (σ_{xv} =+1) modes

ad ad		$\mathbf{k} = k\hat{x}$	E_x	E_y	E_z	H_x	H_y	H_z
$q\sin\frac{q}{2} - \chi_1\cos\frac{q}{2} = 0$	TE, $\sigma_{xy} = +1$	$\overline{\mathrm{TE}, \sigma_{xy} = +1}$	*	+	*	_	*	+
$q\cos\frac{qd}{2} + \chi_1\sin\frac{qd}{2} = 0$	TE, $\sigma_{xy} = -1$	TE, $\sigma_{xy} = -1$	*	_	*	+	*	_
$\frac{q}{\bar{\epsilon}_2}\cos\frac{qd}{2} + \frac{\chi_1}{\bar{\epsilon}_1}\sin\frac{qd}{2} = 0$	TM, $\sigma_{xy} = +1$	TM, $\sigma_{xy} = +1$	+	*	_	*	_	*
$\frac{q}{\bar{\epsilon}_2}\sin\frac{qd}{2} - \frac{\chi_1}{\bar{\epsilon}_1}\cos\frac{qd}{2} = 0$	TM, $\sigma_{xy} = -1$	TM, $\sigma_{xy} = -1$	_	*	+	*	+	*

Low-lying photonic modes are dominated by lowest-order modes of the effective waveguide:

 $σ_{xy}$ =+1 modes are dominated by TE waveguide modes → **quasi-TE** $σ_{xy}$ =-1 modes are dominated by TM waveguide modes → **quasi-TM** However, in general, any PhC mode contains both TE and TM waveguide modes → only the symmetry labels $σ_{xy}$ =±1 have a rigorous meaning.

1. Required notions

- Basic properties of photonic band structure
- •Plane-wave expansion
- •Dielectric slab waveguide
- Waveguide-embedded photonic crystals

2. Guided-mode expansion method

- •Photonic mode dispersion
- Intrinsic diffraction losses
- ·Convergence tests, comparison with other methods
- •Examples of applications

Diffraction losses: the photonic Golden Rule

Modes above the light line are coupled to radiative PhC slab modes. Time-dependent perturbation theory, like in Fermi's golden rule for quantum mechanics, yields an imaginary part of the frequency

$$-\operatorname{Im}\left(\frac{\omega_{k}^{2}}{c^{2}}\right) = \pi \sum_{\mathbf{G}',\lambda,j} |H_{\mathbf{k},\mathrm{rad}}|^{2} \rho_{j}\left(\mathbf{k}+\mathbf{G}';\frac{\omega^{2}}{c^{2}}\right).$$

The matrix element between a quasi-guided and a radiative mode is

$$H_{\mathbf{k},\mathrm{rad}} = \int \frac{1}{\varepsilon(\mathbf{r})} (\nabla \times \mathbf{H}_{\mathbf{k}}^{*}(\mathbf{r})) \cdot (\nabla \times \mathbf{H}_{\mathbf{k}+\mathbf{G}',\lambda,j}^{\mathrm{rad}}(\mathbf{r})) d\mathbf{r}$$

The sum is over

G' \rightarrow reciprocal lattice vectors (out-of-plane diffraction channels) λ =TE, TM \rightarrow polarization of radiative PhC slab modes j=1,3 \rightarrow radiative modes that are outgoing in medium 1,3

Main approximation: radiative PhC slab modes are replaced with those of the effective waveguide.

Photonic DOS and scattering states

The 1D photonic density of states at fixed in-plane wavevector is

$$\rho_{j}\left(\mathbf{g};\frac{\omega^{2}}{c^{2}}\right) = \int_{0}^{\infty} \frac{dk_{z}}{2\pi} \delta\left(\frac{\omega^{2}}{c^{2}} - \frac{g^{2} + k_{z}^{2}}{\overline{\varepsilon}_{j}}\right) = \frac{(\overline{\varepsilon}_{j})^{1/2}c}{4\pi} \frac{\theta(\omega^{2} - \frac{c^{2}\mathbf{g}^{2}}{\overline{\varepsilon}_{j}})}{(\omega^{2} - \frac{c^{2}\mathbf{g}^{2}}{\overline{\varepsilon}_{j}})^{1/2}}$$

It depends only on the asymptotic form of the fields, for scattering states with a single **outgoing** component:



Coupling matrix element

Using the guided-mode expansion for the magnetic field of a PhC slab mode, the matrix element with a radiative mode is

$$H_{\mathbf{k},\mathrm{rad}} = \sum_{\mathbf{G},\alpha} c(\mathbf{k} + \mathbf{G},\alpha)^* H_{\mathrm{guided},\mathrm{rad}}$$

where

$$H_{\mathbf{k},\mathrm{rad}} = \int \frac{1}{\varepsilon(\mathbf{r})} (\nabla \times \mathbf{H}_{\mathbf{k}}^{*}(\mathbf{r})) \cdot (\nabla \times \mathbf{H}_{\mathbf{k}+\mathbf{G}',\lambda,j}^{\mathrm{rad}}(\mathbf{r})) d\mathbf{r}$$

are matrix elements between guided and radiation modes of the effective waveguide, which are calculated analytically.

Both guided and radiation modes are normalized according to

$$\int \mathbf{H}_{\mu}^{*}(\mathbf{r}) \cdot \mathbf{H}_{V}(\mathbf{r}) d\mathbf{r} = \delta_{\mu V}$$

(within a large box for radiation modes).

Quality factor and propagation loss

The quality factor of a photonic mode is defined as

$$Q = \frac{\omega}{2 \operatorname{Im}(\omega)}$$

Spatial attenuation is described by an imaginary part of the wavevector:

$$\operatorname{Im}(k) = \frac{\operatorname{Im}(\omega)}{v_{g}},$$
$$v_{g} = \frac{d\omega}{dk}$$

where

is the mode group velocity. Propagation losses in decibels are obtained as

$$Loss = 4.34 \cdot 2 \operatorname{Im}(k).$$

To treat line and point defects (linear waveguides and nanocavities):

use a supercell

Discussion of GME method (losses)

Main drawback: radiative PhC slab modes are replaced with those of the effective homogeneous waveguide

\Rightarrow the calculation of losses is an APPROXIMATE one

Main advantage: diffraction losses are calculated by perturbation theory \rightarrow the procedure is numerically very efficient (little additional effort beyond photonic mode dispersion).

Calculated values are more accurate when diffraction losses are small \rightarrow good for line defects and for high-Q nanocavities.

The method can be extended to disorder-induced losses of trulyguided modes below the light line.

1. Required notions

- Basic properties of photonic band structure
- •Plane-wave expansion
- •Dielectric slab waveguide
- Waveguide-embedded photonic crystals

2. Guided-mode expansion method

- Photonic mode dispersion
- Intrinsic diffraction losses
- •Convergence tests, comparison with other methods
- •Examples of applications

Convergence tests



Comparison with MIT code

Triangular lattice on membrane, ε =12, d/a=0.6, r/a=0.45



Comparison with FDTD*



*T. Ochiai and K. Sakoda, PRB 63, 125107 (2001)

Comparison with Fourier-modal method (scattering-matrix)

Triangular lattice on membrane, ε =12, d/a=0.3, r/a=0.24



N.b. Along main symmetry directions: vertical parity symmetry σ_{kz}

Losses in W1 waveguide: a comparison



1. Required notions

- ·Basic properties of photonic band structure
- •Plane-wave expansion
- •Dielectric slab waveguide
- Waveguide-embedded photonic crystals

2. Guided-mode expansion method

- •Photonic mode dispersion
- Intrinsic diffraction losses
- •Convergence tests, comparison with other methods
- •Examples of applications

Applications of GME method

- •Photonic band dispersion and gap maps: 1D and 2D lattices
- •Linear waveguides: propagation losses
- •Photonic crystal nanocavities: Q-factors
- •Geometry optimization, design, comparison with expts...
- •Radiation-matter interaction: exciton-polaritons, strong coupling
- •Extrinsic losses: effects of disorder

Main reference on the method:

L.C. Andreani and D. Gerace, Phys. Rev. B 73, 235114 (15 June 2006)

Triangular lattice with triangular holes



Dielectric mirror in a membrane: 1D PhC slab



Gap maps in 1D PhC slabs



• Gap maps for PhC slabs must consider both the modes below and above the light line. Important for the design of structures with defect modes

• Very different behavior as compared to the reference ideal 1D system: no complete band gap, TE/TM splitting

D. Gerace and LCA, Phys. Rev. E 69, 056603 (2004)

SOI photonic crystal slabs: fabrication procedure

(D. Peyrade, M. Belotti and Y. Chen, LPN Marcoussis)



Sample L4

Reflectance and ATR on 1D SOI PhC slabs

In-plane wavevector $k_{\parallel}=n(\omega/c)\sin\theta+G \rightarrow photonic bands$



Photonic mode dispersion: air bridge



Red (blue) lines \rightarrow bands that are even (odd) with respect to reflection in the *xy* plane. Dotted lines \rightarrow dispersion of light in the effective core material and in air. Notice the vertical confinement effect, which increases with decreasing core thickness. Below the light line, good agreement with S.G. Johnson et al., PRB **60**, 5751 (1999).



Gap maps: triangular lattice in air bridge

Notice the confinement effect of the even gap with respect to the ideal 2D case and the absence of a full photonic band gap in a waveguide. For d/a=0.6 the cutoff energy of a second-order mode is plotted.

L.C. Andreani and M. Agio, IEEE-JQE 38, 891 (2002)

2D triangular lattice: complex energies (3D plot)



Air bridge, *d*=0.3*a*, *r/a*=0.3.

The radiative width of quasiguided modes increases for some modes close to the light line, due to the 1D DOS.

At the Γ point, only the dipoleallowed mode has nonzero radiative width.

Phys. Status Solidi (b) 234, 139 (2002)

Complex energies vs. reflectivity



Air bridge d=0.3a, triangular lattice of holes r=0.3a, ΓK , TM polarization. Positions and *linewidths* of spectral structures \rightarrow *real* and *imaginary* parts of energy.

Synt. Met. 139, 695 (2003)

Trends: losses as a function of ...



Radiative width of dipole-allowed mode at the Γ point. The losses increase with the dielectric contrast between core and cladding and with the air fraction of the 2D lattice. Agreement with the model of H. Benisty et al, APL **76**, 532 (2000).

Linear waveguides in 2D PhC slabs



Propagation losses of truly guided modes in Si membranes (extrinsic):

~ 0.6 dB/mm

(Notomi et al., Vlasov et al.)



ε=12, d/a=0.5, r/a=0.28, a=400 nm





LCA and M. Agio, Appl. Phys. Lett. 82, 2011 (2003)





Photonic crystal nanocavities



Point defects in PC slabs behave as 0D cavities with full photonic confinement in very small volumes. The Q-factor can be increased by shifting the positions of nearby holes. Q=45'000 has been measured: T. Akahane, T. Asane, B.S. Song, and S. Noda, Nature 425, 944 (2003).



Q-factor of photonic crystal cavities





Supercell in two directions + Golden Rule \rightarrow Im(ω) and Q= ω /2Im(ω)

*Expt: T. Akahane et al., Nature 425, 944 (2003).

LCA, D. Gerace and M. Agio, Photonics and Nanostruc. 2, 103 (2004)

A model of disorder: size variations

Random distribution of hole radii within a large supercell:

$$P(r) = \exp\left(-\frac{(r-\bar{r})^2}{2\sigma^2}\right)$$

 $\sigma \equiv \Delta r = r.m.s.$ deviation

Dielectric perturbation $\Delta \varepsilon(\mathbf{r}) = \varepsilon_{dis}(\mathbf{r}) - \varepsilon(\mathbf{r})$ couples guided modes to leaky waveguide modes \rightarrow losses by perturbation theory:

$$-\operatorname{Im}\left(\frac{\omega_{k}^{2}}{c^{2}}\right) = \pi \left| \int \frac{1}{\varepsilon_{\operatorname{dis}}(\mathbf{r})} \nabla \times \mathbf{H}_{\operatorname{leaky}}^{*} \cdot \nabla \times \mathbf{H}_{\operatorname{guided}} \, \mathrm{d}\mathbf{r} \right|^{2} \rho\left(\mathbf{k}; \frac{\omega^{2}}{c^{2}}\right)$$

Propagation loss:

 $2 \operatorname{Im}(k) = 2 \frac{\operatorname{Im}(\omega_k)}{v_g}, \qquad v_g = \frac{\mathrm{d}\omega_k}{\mathrm{d}k}$

Dependence on disorder parameter



The losses show a quadratic behavior as a function of the disorder parameter...typical of Rayleigh scattering

D. Gerace and L.C. Andreani, Opt. Lett. 29, 1897 (2004)





^[1]S.J. McNab, N. Moll, Yu. Vlasov, Optics Express 11, 2923 (2003)

Line-defects with increased channel width



Conclusions

➤The GME method is APPROXIMATE for both the photonic mode dispersion (as the basis set does not contain radiative modes of the effective waveguide) and for the losses (because radiative PhC modes are replaced with those of the effective waveguide).

≻The results are close to those of "exact" methods in many common situation. The GME method is most reliable for high index-contrast PhC slabs (membranes, SOI) and for not too high air fractions.

➢Main advantages: computational efficiency (especially in the case of low losses: high-Q nanocavities...) and physical insight when comparing with ideal 2D and homogeneous waveguide systems.

Possible extensions (some underway):

- Improve upon the approximations
- PhC slabs with more than three layers
- Radiation-matter interaction
- Disorder-induced losses...

Appendix: matrix elements etc.

Basis set for guided-mode expansion

Let us denote by

 $\mathbf{g} = g\hat{g}$ the 2D wavevector in the xy plane with modulus g

 $\hat{\varepsilon}_{\mathbf{g}} = \hat{z} \times \hat{g}$ a unit vector perpendicular to both \hat{g} and \hat{z}

 ω_g

the frequency of a guided mode

$$\chi_1 = \left(g^2 - \overline{\varepsilon}_1 \frac{\omega_g^2}{c^2}\right)^{1/2}, \quad q = \left(\overline{\varepsilon}_2 \frac{\omega_g^2}{c^2} - g^2\right)^{1/2}, \quad \chi_3 = \left(g^2 - \overline{\varepsilon}_1 \frac{\omega_g^2}{c^2}\right)^{1/2}$$

The guided modes frequencies of the effective waveguide are found from

$$q(\chi_1 + \chi_3)\cos(qd) + (\chi_1\chi_3 - q^2)\sin(qd) = 0, \qquad \text{TE modes}$$

$$\frac{q}{\overline{\varepsilon}_2}(\frac{\chi_1}{\overline{\varepsilon}_1} + \frac{\chi_3}{\overline{\varepsilon}_3})\cos(qd) + (\frac{\chi_1}{\overline{\varepsilon}_1}\frac{\chi_3}{\overline{\varepsilon}_3} - \frac{q^2}{\overline{\varepsilon}_2^2})\sin(qd) = 0, \qquad \text{TM modes}$$

Guided mode profile: TE

$$\mathbf{E}_{\mu}^{\text{guided}}(\boldsymbol{\rho}, z) = \frac{e^{i\mathbf{g}\cdot\boldsymbol{\rho}}}{\sqrt{S}} i \frac{\omega_{\mu}}{c} \hat{\epsilon}_{\mathbf{g}} \begin{cases} A_{3\mu} e^{-\chi_{3\mu}(z-d/2)}, & z > \frac{d}{2} \\ A_{2\mu} e^{iq_{\mu}z} + B_{2\mu} e^{-iq_{\mu}z}, & |z| < \frac{d}{2} \\ B_{1\mu} e^{\chi_{1\mu}(z+d/2)}, & z < -\frac{d}{2} \end{cases}$$
(A1)

$$\mathbf{H}_{\mu}^{\text{guided}}(\boldsymbol{\rho}, z) = \frac{e^{i\mathbf{g}\cdot\boldsymbol{\rho}}}{\sqrt{S}} \begin{cases} A_{3\mu}(\chi_{3\mu}\hat{g} + ig\hat{z})e^{-\chi_{3\mu}(z-d/2)}, & z > \frac{d}{2} \\ A_{2\mu}i(-q_{\mu}\hat{g} + g\hat{z})e^{iq_{\mu}z} + B_{2\mu}i(q_{\mu}\hat{g} + g\hat{z})e^{-iq_{\mu}z}, & |z| < \frac{d}{2} \\ B_{1\mu}(-\chi_{1\mu}\hat{g} + ig\hat{z})e^{\chi_{1\mu}(z+d/2)}, & z < -\frac{d}{2} \end{cases}$$
(A2)

$$A_{2} = \frac{B_{1}}{2q}(q - i\chi_{1})e^{iqd/2}$$

$$B_{2} = \frac{B_{1}}{2q}(q + i\chi_{1})e^{-iqd/2}$$

$$A_{3} = \frac{B_{1}}{2q\chi_{3}}[q(\chi_{3} - \chi_{1})\cos(qd) + (q^{2} + \chi_{1}\chi_{3})\sin(qd)]$$

$$\frac{\chi_1^2 + g^2}{2\chi_1} |B_1|^2 + \frac{\chi_3^2 + g^2}{2\chi_3} |A_3|^2 + d\left[(g^2 + q^2)(|A_2|^2 + |B_2|^2) + (g^2 - q^2)(A_2^*B_2 + B_2^*A_2) \frac{\sin(qd)}{qd} \right] = 1$$

Guided mode profile: TM

$$\mathbf{H}_{\mu}^{\text{guided}}(\boldsymbol{\rho}, z) = \frac{e^{i\mathbf{g}\cdot\boldsymbol{\rho}}}{\sqrt{S}} \hat{\epsilon}_{\mathbf{g}} \begin{cases} C_{3\mu} e^{-\chi_{3\mu}(z-d/2)}, & z > \frac{d}{2} \\ C_{2\mu} e^{iq_{\mu}z} + D_{2\mu} e^{-iq_{\mu}z}, & |z| < \frac{d}{2} \\ D_{1\mu} e^{\chi_{1\mu}(z+d/2)}, & z < -\frac{d}{2} \end{cases}$$
(A7)

$$\mathbf{E}_{\mu}^{\text{guided}}(\boldsymbol{\rho}, z) = \frac{e^{i\mathbf{g}\cdot\boldsymbol{\rho}}}{\sqrt{S}} i \frac{c}{\omega_g} \begin{cases} \frac{1}{\bar{\epsilon}_3} C_{3\mu}(\chi_{3\mu}\hat{g} + ig\hat{z})e^{-\chi_{3\mu}(z-d/2)}, & z > \frac{d}{2} \\ \frac{1}{\bar{\epsilon}_2} [C_{2\mu}i(-q_{\mu}\hat{g} + g\hat{z})e^{iq_{\mu}z} + D_{2\mu}i(q_{\mu}\hat{g} + g\hat{z})e^{-iq_{\mu}z}], & |z| < \frac{d}{2} \\ \frac{1}{\bar{\epsilon}_1} D_{1\mu}(-\chi_{1\mu}\hat{g} + ig\hat{z})e^{\chi_{1\mu}(z+d/2)}, & z < -\frac{d}{2} \end{cases}$$
(A8)

The appropriate relations between coefficients can be derived from (A3)-(A5) by the replacements $A \to C$, $B \to D$ and $\chi_1 \to \chi_1/\bar{\epsilon}_1$, $q \to q/\bar{\epsilon}_2$ (except in the trigonometric functions), $\chi_3 \to \chi_3/\bar{\epsilon}_3$. The normalization integral of the magnetic field gives the condition

$$\frac{|D_1|^2}{2\chi_1} + \frac{|C_3|^2}{2\chi_3} + d\left[|C_2|^2 + |D_2|^2 + (C_2^*D_2 + D_2^*C_2)\frac{\sin(qd)}{qd}\right] = 1.$$
(A9)

Matrix elements between guided modes

$$\begin{aligned} \mathcal{H}_{\mu\nu}^{\text{TE-TE}} &= \left(\frac{\omega_{\mu}}{c}\right)^{2} \left(\frac{\omega_{\nu}}{c}\right)^{2} \hat{\epsilon}_{g} \cdot \hat{\epsilon}_{g'} \left\{ (\bar{\epsilon}_{1})^{2} \eta_{1}(\mathbf{G},\mathbf{G}') B_{1\mu}^{*} B_{1\nu} I_{1} + (\bar{\epsilon}_{3})^{2} \eta_{3}(\mathbf{G},\mathbf{G}') A_{3\mu}^{*} A_{3\nu} I_{3} \right. \\ &\left. + (\bar{\epsilon}_{2})^{2} \eta_{2}(\mathbf{G},\mathbf{G}') \left[(A_{2\mu}^{*} A_{2\nu} + B_{2\mu}^{*} B_{2\nu}) I_{2-} + (A_{2\mu}^{*} B_{2\nu} + B_{2\mu}^{*} A_{2\nu}) I_{2+} \right] \right\}, \end{aligned}$$

 $\begin{aligned} \mathcal{H}_{\mu\nu}^{\rm TM-TM} \ &= \ \eta_1(\mathbf{G},\mathbf{G}')D_{1\mu}^*D_{1\nu}(\chi_{1\mu}\chi_{1\nu}\hat{g}\cdot\hat{g}'+gg')I_1 + \eta_3(\mathbf{G},\mathbf{G}')C_{3\mu}^*C_{3\nu}(\chi_{3\mu}\chi_{3\nu}\hat{g}\cdot\hat{g}'+gg')I_3 \\ &+ \eta_2(\mathbf{G},\mathbf{G}')\left[(C_{2\mu}^*C_{2\nu}+D_{2\mu}^*D_{2\nu})(q_\mu q_\nu\hat{g}\cdot\hat{g}'+gg')I_{2-} + (C_{2\mu}^*D_{2\nu}+D_{2\mu}^*C_{2\nu})(-q_\mu q_\nu\hat{g}\cdot\hat{g}'+gg')I_{2+}\right],\end{aligned}$

$$\mathcal{H}_{\mu\nu}^{\mathrm{TE-TM}} = \left(\frac{\omega_{\mu}}{c}\right)^{2} \hat{\epsilon}_{\mathbf{g}} \cdot \hat{g}' \left\{ -\bar{\epsilon}_{1} \eta_{1}(\mathbf{G}, \mathbf{G}') B_{1\mu}^{*} D_{1\nu} \chi_{1\nu} I_{1} + \bar{\epsilon}_{3} \eta_{3}(\mathbf{G}, \mathbf{G}') A_{3\mu}^{*} C_{3\nu} \chi_{3\nu} I_{3} \right. \\ \left. + i \bar{\epsilon}_{2} \eta_{2}(\mathbf{G}, \mathbf{G}') q_{\nu} \left[(-A_{2\mu}^{*} C_{2\nu} + B_{2\mu}^{*} D_{2\nu}) I_{2-} + (A_{2\mu}^{*} D_{2\nu} - B_{2\mu}^{*} C_{2\nu}) I_{2+} \right] \right\},$$

$$\mathcal{H}_{\mu\nu}^{\mathrm{TM-TE}} = \left(\frac{\omega_{\nu}}{c}\right)^{2} \hat{g} \cdot \hat{\epsilon}_{\mathbf{g}'} \left\{ -\bar{\epsilon}_{1} \eta_{1}(\mathbf{G}, \mathbf{G}') D_{1\mu}^{*} B_{1\nu} \chi_{1\mu} I_{1} + \bar{\epsilon}_{3} \eta_{3}(\mathbf{G}, \mathbf{G}') C_{3\mu}^{*} A_{3\nu} \chi_{3\mu} I_{3} \right. \\ \left. -i\bar{\epsilon}_{2} \eta_{2}(\mathbf{G}, \mathbf{G}') q_{\mu} \left[\left(-C_{2\mu}^{*} A_{2\nu} + D_{2\mu}^{*} B_{2\nu} \right) I_{2-} + \left(D_{2\mu}^{*} A_{2\nu} - C_{2\mu}^{*} B_{2\nu} \right) I_{2+} \right] \right\}.$$

$$I_1 = (\chi_{1\mu} + \chi_{1\nu})^{-1}, \ I_{2\pm} = \frac{\sin((q_\mu \pm q_\nu)d/2)}{(q_\mu \pm q_\nu)/2}, \ I_3 = (\chi_{3\mu} + \chi_{3\nu})^{-1}$$

→ diel. tensor

Radiative mode profiles

$$q_j = \left(\bar{\epsilon}_j \frac{\omega^2}{c^2} - g^2\right)^{1/2}, \ j = 1, 2, 3.$$
 $\hat{\epsilon}_{\mathbf{g}} = \hat{z} \times \hat{g}$ $z_1 = -d/2, \ z_2 = 0, \ z_3 = d/2$

TE modes. Normalization: $W_1 = 0, X_1 = 1/\sqrt{\overline{\epsilon_1}}$ or $W_3 = 1/\sqrt{\overline{\epsilon_3}}, X_3 = 0.$ $\mathbf{E}_j^{\mathrm{rad}}(\rho, z) = \frac{e^{i\mathbf{g}\cdot\rho}}{\sqrt{S}} i\hat{\epsilon}_{\mathbf{g}} \left[W_j e^{iq_j(z-z_j)} + X_j e^{-iq_j(z-z_j)} \right], \quad (D2)$

$$\mathbf{H}_{j}^{\mathrm{rad}}(\boldsymbol{\rho}, z) = \frac{e^{i\mathbf{g}\cdot\boldsymbol{\rho}}}{\sqrt{S}} i \frac{c}{\omega} \left[(g\hat{z} - q_{j}\hat{g}) W_{j} e^{iq_{j}(z-z_{j})} + (g\hat{z} + q_{j}\hat{g}) X_{j} e^{-iq_{j}(z-z_{j})} \right].$$
(D3)

TM modes. Normalization:
$$Y_1 = 0, Z_1 = 1$$
 or $Y_3 = 1, Z_3 = 0.$

$$\mathbf{H}_j^{\mathrm{rad}}(\rho, z) = \frac{e^{i\mathbf{g}\cdot\rho}}{\sqrt{S}} \hat{\epsilon}_{\mathbf{g}} \left[Y_j e^{iq_j(z-z_j)} + Z_j e^{-iq_j(z-z_j)} \right], \quad (D6)$$

$$\mathbf{E}_{j}^{\mathrm{rad}}(\boldsymbol{\rho}, z) = -\frac{e^{i\mathbf{g}\cdot\boldsymbol{\rho}}}{\sqrt{S}} \frac{c}{\bar{\epsilon}_{j}\omega} \left[(g\hat{z} - q_{j}\hat{g})Y_{j}e^{iq_{j}(z-z_{j})} + (g\hat{z} + q_{j}\hat{g})Z_{j}e^{-iq_{j}(z-z_{j})} \right].$$
(D7)

N.b. when q_j is imaginary, the mode does not contribute to losses.

Matrix elements guided \leftrightarrow radiative

$$\mathcal{H}_{\mu,r}^{\text{TE}-\text{TE}} = \left(\frac{\omega_{\mu}}{c}\right)^{2} \frac{\omega_{r}}{c} \hat{\epsilon}_{\mathbf{g}} \cdot \hat{\epsilon}_{\mathbf{g}'} \times \left\{ (\bar{\epsilon}_{1})^{2} \eta_{1}(\mathbf{G}, \mathbf{G}') B_{1\mu}^{*}(W_{1r}I_{1+} + X_{1r}I_{1-}) + (\bar{\epsilon}_{3})^{2} \eta_{3}(\mathbf{G}, \mathbf{G}') A_{3\mu}^{*}(W_{3r}I_{3-} + X_{3r}I_{3+}) \right. \\ \left. + (\bar{\epsilon}_{2})^{2} \eta_{2}(\mathbf{G}, \mathbf{G}') \left[(A_{2\mu}^{*}W_{2r} + B_{2\mu}^{*}X_{2r}) I_{2-} + (A_{2\mu}^{*}X_{2r} + B_{2\mu}^{*}W_{2r}) I_{2+} \right] \right\}, \qquad (E1)$$

$$\mathcal{H}_{\mu,r}^{\mathrm{TM-TM}} = \eta_1(\mathbf{G}, \mathbf{G}') D_{1\mu}^* [(gg' + i\chi_{1\mu}q_{1r}\hat{g} \cdot \hat{g}')Y_{1r}I_{1+} + (gg' - i\chi_{1\mu}q_{1r}\hat{g} \cdot \hat{g}')Z_{1r}I_{1-}] + \eta_3(\mathbf{G}, \mathbf{G}') C_{3\mu}^* [(gg' - i\chi_{3\mu}q_{3r}\hat{g} \cdot \hat{g}')Y_{3r}I_{3-} + (gg' + i\chi_{3\mu}q_{3r}\hat{g} \cdot \hat{g}')Z_{3r}I_{3+}]$$

 $+\eta_{2}(\mathbf{G},\mathbf{G}')\left[(C_{2\mu}^{*}Y_{2r}+D_{2\mu}^{*}Z_{2r})(gg'+q_{\mu}q_{2r}\hat{g}\cdot\hat{g}')I_{2-}+(C_{2\mu}^{*}Z_{2r}+D_{2\mu}^{*}Y_{2r})(gg'-q_{\mu}q_{2r}\hat{g}\cdot\hat{g}')I_{2+}\right],(\mathbf{E2})$

$$\mathcal{H}_{\mu,r}^{\text{TE-TM}} = i \left(\frac{\omega_{\mu}}{c}\right)^{2} \hat{\epsilon}_{\mathbf{g}} \cdot \hat{g}' \left\{ \bar{\epsilon}_{1} \eta_{1}(\mathbf{G}, \mathbf{G}') q_{1r} B_{1\mu}^{*}(-Y_{1r}I_{1+} + Z_{1r}I_{1-}) + \bar{\epsilon}_{3} \eta_{3}(\mathbf{G}, \mathbf{G}') q_{3r} A_{3\mu}^{*}(-Y_{3r}I_{3-} + Z_{3r}I_{3+}) \right. \\ \left. + \bar{\epsilon}_{2} \eta_{2}(\mathbf{G}, \mathbf{G}') q_{2r} \left[(-A_{2\mu}^{*}Y_{2r} + B_{2\mu}^{*}Z_{2r}) I_{2-} + (A_{2\mu}^{*}Z_{2r} - B_{2\mu}^{*}Y_{2r}) I_{2+} \right] \right\},$$
(E3)

$$\mathcal{H}_{\mu,r}^{\mathrm{TM-TE}} = \frac{\omega_r}{c} \hat{g} \cdot \hat{\epsilon}_{\mathbf{g}'} \left\{ -\bar{\epsilon}_1 \eta_1(\mathbf{G}, \mathbf{G}') \chi_{1\mu} D_{1\mu}^* (W_{1r} I_{1+} + X_{1r} I_{1-}) + \bar{\epsilon}_3 \eta_3(\mathbf{G}, \mathbf{G}') \chi_{3\mu} C_{3\mu}^* (W_{3r} I_{3-} + X_{3r} I_{3+}) \right. \\ \left. -i\bar{\epsilon}_2 \eta_2(\mathbf{G}, \mathbf{G}') q_\mu \left[(D_{2\mu}^* X_{2r} - C_{2\mu}^* W_{2r}) I_{2-} + (D_{2\mu}^* W_{2r} - C_{2\mu}^* X_{2r}) I_{2+} \right] \right\}.$$
(E4)

$$I_{3\pm} = (\chi_{3\mu} \pm iq_{3r})^{-1}, \ I_{2\pm} = \frac{\sin((q_{\mu} \pm q_{2r})d/2)}{(q_{\mu} \pm q_{2r})/2}, \ I_{1\pm} = (\chi_{1\mu} \pm iq_{1r})^{-1}.$$

$$\rightarrow$$
 coupling